Quality Management ISO 9001



Coding Approved Page TDGR107EN 24.01.2020 1 of 2

Technical Datasheet

Eurospan E1 P2 CE EAC (Rec. 107) Eurospan E1 P2 CE ECS (Rec. 1) Eurospan E1 P2 CE ELS (Rec. 108)

EAC (Egger Audit Controlled): Made from certified wood and controlled sources, suitable for FSC®-certified products. ECS (Egger Controlled Sources): Made from certified wood and controlled sources, suitable for PEFC certified products. ELS (Egger Legal Sources): Wood from controlled sources according to EUTR.

Certification statement (claim) on the sales documents is only on customer's request and according to availability.

Board type P2 according to EN 312

Mechanical properties Board mean values	Unit	Board thickness					
	[mm]	>6 - 13	>13 - 20	>20 - 25	>25 - 32	>32 - 40	
Density EN 323	[kg/m³]	specific to plant					
Internal bond EN 319	[N/mm²]	0.40	0.35	0.30	0.25	0.20	
Bending strength EN 310	[N/mm²]	11.0	11.0	10.5	9.5	8.5	
Bending modulus of elasticity EN 310	[N/mm²]	1800	1600	1500	1350	1200	
Surface soundness EN 311	[N/mm²]	0.95					
Board moisture* EN 322	[%]	4 - 13					
Formaldehyde emission class(es)**		E1					

General tolerances	Unit	Board thickness					
	[mm]	>6 - 13	>13 - 20	>20 - 25	>25 - 32	>32 - 40	
Length and width tolerance EN 324	[mm]	±5.0					
Squareness EN 324	[mm/m]	<=2.0					
Edge straightness tolerance EN 324	[mm/m]	<=1.5					
Thickness tolerance EN 324	[mm]	±0.3					
Tolerance on the mean density EN 323	[%]	±10					

MORE FROM WOOD.

Quality Management ISO 9001



Coding Approved Page TDGR107EN 24.01.2020 2 of 2

Building physical properties	ding physical properties Unit						
	[mm]	>6 - 13	>13 - 20	>20 - 25	>25 - 32	>32 - 40	
Fire behaviour category			1				
In line with EN13986 (9mm) and density 600 kg/m³		D-s2, d0					
Water vapour diffusion resistance value							
Mean bulk density 600 kg/m³ Mean bulk density 900 kg/m³			μ moist 15 20		μ dry 50 50		
Thermal conductivity EN 13986							
Mean bulk density 600 kg/m ³ Mean bulk density 900 kg/m ³	[W/(m*K)]	0.12 0.18					
Air sound insulation EN 13986							
EN 13986		R = 13 x lg(mA) + 14 (mA = board weight per unit area kg/m²)					
Sound absorption EN 13986							
Frequency range 250 Hz bis 500 Hz 1000 Hz bis 2000 Hz		0.1 0.25					
Biological durability EN 13986							
EN 335-3		Hazard class 1 (without earth contact, dry 20°C / 65% relative humidity)					
PCP content EN 13986							
EN 13986	[ppm]			<5			

* On delivery

** The product complies with the following emission class(es):

E1: According to EN 13986+A1:2015-04 formaldehyde class E1, wood based panels must not exceed a perforator value according to EN ISO 12460-5 of 8 mg HCHO/100g oven dry board.

Compliant with German ChemVerbotsV only as Eurodekor or with applicable coating/covering.

Provisional note:

This technical data sheet has been carefully drawn up to the best of our knowledge. We accept no liability for any mistakes, errors in standards or printing errors. In addition, technical modifications can result from the continuous further development, as well as from changes in standards and documents originating from statutory bodies. The contents of this technical leaflet should therefore not be considered as instructions for use or as legally binding.